

# **ARDEX AF365**

# **Timber Adhesive For Teakwood Floor**

Ready to use

Excellent initial wet tack and grab

Good bond strength

Gap filing function for sub-floor installations



ARDEX Singapore Pte Ltd 26 Tuas Ave 4 Singapore 639376 Ph: +65 6861 7700

Fax: + 65 6862 3381 Email: sales@ardex.com.sg Website: www.ardex.com.sg

# **ARDEX AF365**

# **Timber Adhesive For Teakwood Floor**

# **DESCRIPTION**

ARDEX AF365 is a single-component, PVA polymer based emulsion adhesive for bonding plywood sub-floor, teak wood strip. It adhere to most types of wood, parquet and sheet timber flooring systems to concrete, timber or over existing floor

# **SPECIAL PROPERTIES**

- Ready to use
- Excellent initial wet tack and grab
- Good bond strength
- Gap filing function for sub-floor installations

### **APPLICATION**

- Bonding plywood sub-floor onto concrete and cement screed
- Teakwood and parquet bonding
- As a universal wood adhesive, to bond most porous materials together

# **SURFACE PREPARATION**

All substrates must be level, smooth, permanently dry, structurally sound, firm, load-bearing, free from curing compounds, cracks and also have free of excess mositure/alkali and all substances (oil, wax, grease, paint, oil based sealers and etc.) Concrete surfaces should be free from laitance which, if present, should be removed by scabbling or grit blasting to produce a sound surface.

# DIRECTIONS FOR USE MIXING

Adhesive can be used neat or with little of water dilution, approximately 3% by weight.

# **APPLICATION**

ARDEX AF 365 should be applied evenly to the suitablility prepared substrate using a notch trowel. Place wood strips , planks or plywood directly into the wet adhesive firmly, interlocking with tongue or groove of the next strip or plank. Anchor down with concrete nails to hold the wood strips down whilst the adhesive sets.

# **DRYING TIME**

Allow the finished assembly to dry, cure and harden fully at least 7 - 10 days before sanding and application of lacquer.

# **COVERAGE**

Depending on the texture and absorbency of the floor, the coverage will be approx. 25 - 30m<sup>2</sup> per 20kg.

## **PACKAGING**

ARDEX AF365 is available in 20kg carton.

### **STORAGE**

ARDEX AF365 should be stored in cool, dry shaded warehouses, away from rain and sunlight. When stored under the correct conditions, ARDEX AF365 will have a shelf life of 12 months.

# **PRECAUTIONS**

Avoid contact with skin and eyes; in case of contact with the eyes, rinse immediately with plenty of water and seek medical advice; wear suitable gloves and keep the product out of the reach of children.

# **TECHNICAL DATA**

Product Identity

Form: Milk white liquid

Solid content (by weight): > 48.5

Viscosity: 25 - 35 X 10 ⁴ cps

oH: 4 - 6

**ARDEX** materials are also manufactured in Australia, Austria. Denmark, England, Germany, Spain, U.S.A., and represented throughout the world.

#### DISCLAIMER:

The technical datasheets are based on the latest information an d given in good faith and represent the best of our knowledge and experience at the time of printing. They are primarily offered for user's consideration and evaluat ion. It is the responsibility of the user to conduct their own tests to validate the suitability of the products. It is also the responsibility of the user to ensure that the products are used and handled correctly and in accordance with any applicable standards, the product instructions and recommendations and only for the uses they are intended. As we have no control over site conditions and the execution of the work, we accept no liability for any loss or damage which may rise as a result thereof. We also reserve the right to update the information at any time without prior notice to you to reflect our ongoing research and development program.

# Malaysia:

ARDEX MANUFACTURING SDN BHD (669180-X) No. 19-1, Jalan Puteri 2/2, Bandur Puteri, 47100, Puchong, Selangor Darul Ehsan Tel: +603 8060 1139 Fax: +603 8060 0719 Email: sales@ardex.com.sg

### Thailand:

ARDEX (THAILAND) CO., LTD 969 2nd Floor Moo, 13, Soi 45, Bangna-Trad Road Bangkaew, Bangplee, Samutprakarn 10540 Thailand Tel: +66 23163069 Fax: +66 23163075 Email: sales@ardex.co.th

# Vietnam:

Mobile: +84 901 351 308 Email: sales@ardex.com.sg